

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 January 2001 (04.01.2001)

PCT

(10) International Publication Number
WO 01/00404 A1

(51) International Patent Classification⁷: B32B 17/10,
C08J 3/22

(21) International Application Number: PCT/US99/14393

(22) International Filing Date: 25 June 1999 (25.06.1999)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant (for all designated States except US): E. I. DU
PONT DE NEMOURS AND COMPANY [US/US]; 1007
Market Street, Wilmington, DE 19898 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): PHILLIPS, Thomas,
Richard [US/US]; 5114 Glenbrook Drive, Vienna, WV
26105 (US).

(74) Agent: DOBSON, Kevin, S.; E. I. du Pont de Nemours
and Company, Legal Patent Records Center, 1007 Market
Street, Wilmington, DE 19898 (US).

(81) Designated States (national): AE, AL, AU, BA, BB, BG,
BR, CA, CN, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN,
IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX,
NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ,
VN, YU, ZA.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM,
AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT,
BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: COLORED POLYVINYL BUTYRAL INTERLAYER WITH IMPROVED HAZE PROPERTIES

(57) Abstract: A laminar structure comprised of at least two layers of glass and a sheet of plasticized PVB prepared by providing a color concentrate comprised of solid pigmented chips wherein the chips have a preselected size range to minimize haze in the laminated structure and are dispersed in a low molecular weight polyvinyl butyral resin, said chips comprising from about 10 to 60 weight percent of the color concentrate, depositing said color concentrate on a roughened surface of polyvinyl butyral sheeting as a dried colored coating or directly melt incorporating, and thereafter laminating said sheeting between the surfaces of layers of glass.

200220 05808660



WO 01/00404 A1